


Clariant Nylon 6/6

Processing Conditions

- A. Pre-drying** 160~180 F x 2~4 hrs
depending on
- a) Humidity
 - b) Ratio of regrind resin
 - c) Storage conditions

B. Barrel Setting Profile



MAX(F)	550_{NOZZLE}	560_{FRONT}	550_{MIDDLE}	510_{REAR}
MIN(F)	510	540	520	480

- C. Mold Temperature** 130~200F

Notes:

- 1. Injection Pressure - 5000 to 15000 psi**
- 2. Back Pressure - 0.00 to 800 psi**
- 3. Screw Speed - 30 to 90 rpm**
- 4. Suggested Max Regrind - 25%**

*The data presented here are typical values only and may or may not be based upon actual measurements. Technical information contained herein is furnished without charge or obligation, and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, we make no representation about, and is not responsible or liable for the accuracy or reliability of data, nor for the toxicological effects or Industrial Hygiene requirements associated with particular uses of any product described herein. Any properties listed are provided as information only and in no way modify, amend, enlarge, or create any specification or warranty.